



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 033 357 A1**

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
06.09.2000 Bulletin 2000/36

(51) Int Cl.7: **C06B 21/00**, C30B 30/06,
C30B 7/00, B01J 2/18

(21) Application number: **99200592.6**

(22) Date of filing: **02.03.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Veltmans, Wilhelmina H.M.**
4617 GE Bergen op Zoom (NL)
• **Wierckx, Franciscus J.M.**
4621 CH Bergen op Zoom (NL)

(71) Applicant: **AEROSPACE PROPULSION
PRODUCTS B.V.**
4625 DB Bergen op Zoom (NL)

(74) Representative: **Ottevangers, Sietse Ulbe et al**
Vereenigde,
Postbus 87930
2508 DH Den Haag (NL)

(54) **Process for the production of crystalline energetic materials**

(57) The invention is directed to a process for the
production of crystalline energetic materials having im-

proved stability and/or decreased sensitivity by crystal-
lisation of the energetic materials with ultrasonic vibra-
tion having a frequency of between 10 and 100 kHz.

EP 1 033 357 A1

Description

[0001] The invention is directed to a process for the production of crystalline energetic materials having improved stability and sensitivity properties.

[0002] Examples of energetic materials are energetic oxidisers and explosives. High energy oxidisers are used as component in solid propellants for launchers and related applications. Examples of such oxidisers are hydrazinium nitroformate (HNF), nitramine hexaazaisowurtzitane (CL-20), ammonium dinitramide (ADN), ammonium-perchlorate (AP) and the like. Other materials falling in this class of energetic materials are explosives like cyclotrimethylene trinitramine (Hexogen, RDX), cyclotetramethylene tetranitramine (Octogen, HMX) and pentaerythrol tetranitrate (PETN).

[0003] These materials are all produced in a manner, wherein at some time during their preparation a crystallisation step occurs. Sometimes also a purifying recrystallisation step is included in the process. As the final product form of these materials is crystalline, one of the final steps of such a process includes a crystallisation.

[0004] For these crystalline energetic materials stability and sensitivity are very important parameters. Stability is of course important, as it determines the possible shelf life of the material during long term storage, and it further plays a role in the conditions under which the material can be stored and used (wider temperature range of storage and application conditions). More stable materials need less strict conditions for storage and use, or may be stored for a longer period of time under the same conditions.

[0005] The sensitivity, and more in particular the friction sensitivity and the impact sensitivity, are important, as it determines the care that should be taken during handling and transport of the material. Also sensitivity determines to a large extent the governmental restrictions posed on transport and storage.

[0006] It is accordingly one object of the present invention to improve the stability of crystalline energetic materials. It is another object of the invention to improve the sensitivity, such as impact and friction sensitivity thereof.

[0007] These and other objects are realised by the present invention, which comprises a process for the production of crystalline energetic materials having improved stability and/or decreased sensitivity by crystallisation of the energetic materials with ultrasonic vibration having a frequency of between 10 and 100 kHz. Preferably the amplitude of an ultrasonic probe used for producing the vibration is between 0.4 and 10 μm .

[0008] The present invention is based on the surprising discovery, that by carrying out the last crystallisation step in the presence of ultrasonic vibration with a frequency of between 10 and 100 kHz, the morphology, stability and sensitivity can be improved, i.e. the crystals become more rounded, the stability is better and the sensitivity is less.

[0009] In US patent No. 3,222,231 published on December 7, 1965, it is disclosed to improve the morphology of crystalline material, including ammonium perchlorate and hydrazinium nitroformate, by precipitating a solid solute out of solution, while mechanically agitating the solution and subjecting it to a high frequency vibration. According to this patent, the processing under vibration improves the morphology of the crystals. The disclosure of this patent does not indicate anything about the effect of the treatment on stability and sensitivity.

[0010] According to a more preferred embodiment the present invention is directed to an improvement in the production of hydrazinium nitroformate (HNF). HNF belongs to the class of high energy oxidisers and can be used in high performance chlorine free solid propellants.

[0011] HNF is generally produced in crystalline form by combining hydrazine and nitroform under well defined conditions, followed by further purification using i.a. crystallisation. One method for the production of HNF is described in US patent number 5,557,015. According to this method HNF is prepared in very pure form by reacting hydrazine and nitroform in a system that is a solvent for nitroform and a non-solvent for hydrazinium nitroformate, in the presence of a proton transferring medium.

[0012] The stability of the present energetic materials, and more in particular of HNF, can be determined by vacuum thermal stability (VTS) in accordance with STANAG 4479 at 60 and 80°C for 48 to 100 hours.

[0013] The friction sensitivity is determined by BAM friction in accordance with ONU 3b)i), the impact sensitivity by BAM impact in accordance with ONU 3a)ii).

[0014] It has been noted that whereas the HNF crystals are having an aspect ratio of more than 4 after crystallisation without ultrasonic vibration, the crystals produced in accordance with the process of the present invention have an aspect ratio, which is sometimes lower than this, depending both on the applied amplitude of the ultrasonic probe and the recrystallisation method used. However, it has also been found that there is no direct link between the aspect ratio of the crystals on the one hand and the stability or sensitivity on the other hand.

[0015] The process of the present invention can be carried out in various ways. In general it is important that during crystallisation the crystallising mixture is subjected to treatment with the ultrasonic vibration. This process can be applied during crystallisation and during recrystallisation.

[0016] In case of batch processing one may subject the whole batch at the same time to an ultrasonic vibration. In the alternative it can be done by stirring the crystallising mixture in such a way that the batch content moves through a region of ultrasonic vibration sufficiently frequently to obtain the effect. This can for example be done by using an ultrasonic probe, whereby the stirring regime or the construction of the crystalliser is such

that the suspension passes the vibration zone frequently. It is also possible to include the treatment in a recirculation loop of the crystalliser.

[0017] The temperature of the treatment is not critical, although it may have some effect on the actual stability, sensitivity and morphology. Temperatures between 0 and 100°C, preferably between 15 and 75°C can be used.

[0018] The present invention is now explained on the basis of the production of crystalline HNF, although it will be clear to the skilled person that other materials may be produced using the same principles, wherein variation may be applied, if necessary to take into account the actual production methods of other materials, while maintaining the basic principles of the invention.

[0019] In the operation of the present invention first HNF is prepared from hydrazine and nitroform, for example as disclosed in the cited US patent No. 5,557,015, the contents of which is incorporated herein by way of reference. In general this means that nitroform having a purity of more than 98.5 %, dissolved in dichloroethane, and water (6 vol. %) are mixed. At 0°C an equimolar amount of hydrazine, purity 99.5%, is added and the mixture is stirred, while keeping the temperature between 0 and 5°C. The crystalline HNF obtained thereby is then subjected, either in the reaction mixture, or after crystallisation and/or additional purification, to a final (re)crystallisation in the presence of the ultrasonic vibration.

[0020] The invention is now further explained on the basis of a number of examples.

EXAMPLE 1

[0021] Nitroform, dissolved in dichloroethane (23 wt. % nitroform), and water (6 vol. %) are mixed. At 0°C an equimolar amount of hydrazine, purity 99.5%, is added and the mixture is stirred, while keeping the temperature between 0 and 5°C. The crystalline HNF obtained thereby is separated from the mother liquor and redissolved in methanol.

[0022] The HNF solution in methanol is subsequently cooled yielding HNF crystals. This experiment has been performed in the absence of ultrasound (US) (reference, amplitude 0 µm) and under ultrasonic vibration with a frequency of 20 kHz and varying ultrasonic amplitude. Figures 1, 2, 3 and 4 show the properties of HNF crystals obtained in several experiments in which the amplitude of ultrasonic vibration is varied during cooling crystallisation.

[0023] Figure 1 shows the positive effect of ultrasound (US) on the morphology of HNF, expressed as the Length over Diameter (L/D) and average particle size (XspH.).

[0024] Figure 2 shows the positive effect of ultrasound (US) on the sensitivity of HNF, expressed in BAM impact and BAM friction values ([N] and [N.m] respectively).

[0025] Figure 3 shows that ultrasound (US) has a positive

effect on the thermal stability of HNF at 60°C. The initial gas evolution decreases in comparison to the reference sample (no ultrasound (US) = amplitude of 0 µm) and the gas evolution in time decreases as well when a low amplitude of 0.4 µm is applied.

[0026] Figure 4 gives an indication of the positive effect of ultrasound (US) on thermal stability at 80°C. At 80°C the effect becomes more apparent (on the larger gas evolution scale) after -80 hrs. These four figures clearly show the positive effect of ultrasound (US) during cooling crystallisation on morphology, sensitivity and stability in comparison to the reference HNF crystallised in absence of ultrasound (US).

EXAMPLE 2 (ultrasound (US) applied during drowning out crystallisation of HNF)

[0027] HNF is prepared by the method described in example 1. The HNF in methanol solution is subsequently closed in a methylene chloride/methanol solution yielding HNF crystals. This experiment has been performed in the absence of ultrasound (US) (reference, amplitude 0 µm) and under ultrasonic vibration with a frequency of 20 kHz and varying ultrasonic amplitude. Figures 5, 6 and 7 show the properties of HNF crystals obtained in several experiments in which the amplitude of ultrasonic vibration is varied during drowning out crystallisation.

[0028] Figure 5 shows the negative effect of ultrasound (US) on morphology; L/D increases which implies that the HNF crystals are more needle shaped.

[0029] Figures 6 and 7 show VTS results at 60 and 80°C, respectively.

[0030] From figure 6 it can be clearly seen that ultrasound (US) application reduces initial gas evolution with a minimum initial gas evolution at a low to medium ultrasound (US) amplitude (0.4-2 µm).

[0031] Figure 7 shows that at higher temperature (80°C) the application of ultrasound (US) not only reduces the initial gas evolution but also the overall gas evolution rate in time. These three figures clearly show that in spite of the negative influence of ultrasound (US) during drowning-out crystallisation on morphology, ultrasound (US) has a positive influence on stability in comparison to the reference HNF crystallised in absence of ultrasound (US).

Claims

1. Process for the production of crystalline energetic materials having improved stability and/or decreased sensitivity by crystallisation of the energetic materials with ultrasonic vibration having a frequency of between 10 and 100 kHz.
2. Process according to claim 1, wherein the crystallising mixture is stirred during crystallisation.

3. Process according to claim 1 or 2, wherein the crystallising mixture is transported continuously through the zone of ultrasonic vibration.
4. Process according to claims 1-3, wherein the temperature during recrystallisation is between 15 and 75°C. 5
5. Process according to claims 1-4, wherein the ultrasonic vibration is generated using an ultrasonic probe, the amplitude thereof being between 0.4 and 10 µm. 10
6. Process according to claims 1-5, wherein the energetic materials are selected from the group of explosives and high energy oxidisers. 15
7. Process according to claim 6, wherein the said energetic materials are selected from the group consisting of hydrazinium nitroformate, Cl2O, ADN, AP, RDX, HMX and PETN. 20

25

30

35

40

45

50

55




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 20 0592

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION
D,X	US 3 222 231 A (M. MARKELS, JR. ET AL.) 7 December 1965 (1965-12-07)	1,2,4,6,7	C06B21/00 C30B30/06 C30B7/00 B01J2/18
Y	* column 1, line 64 - column 2, line 6 * * column 2, line 40 - column 3, line 8; claims; examples *	5	
A	DE 11 32 847 B (BOMBRINI PARODI-DELFINO SOCIETÀ PER AZIONI) * column 1, line 39 - line 50 *	1	
X	EP 0 275 607 A (NOBEL KEMI AB) 27 July 1988 (1988-07-27)	1-4,6	
Y	* claims; example 3 *	5	
Y	US 5 471 001 A (H.W. ANDERSON ET AL.) 28 November 1995 (1995-11-28) * claims *	5	
A	US 3 513 212 A (J.K. SKREBOWSKI ET AL.) 19 May 1970 (1970-05-19) * claims *	1-7	
A	WO 92 20420 A (E. ACTON ET AL.) 26 November 1992 (1992-11-26) * claims *	1-7	TECHNICAL FIELDS SEARCHED C06B C30B B01J B01D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 13 August 1999	Examiner Schut, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (Rev.01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 20 0592

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-08-1999

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 3222231	A	07-12-1965	NONE		
DE 1132847	B		GB	934536 A	
EP 275607	A	27-07-1988	JP	63294953 A	01-12-1988
			SE	8700213 A	22-07-1988
US 5471001	A	28-11-1995	EP	0797562 A	01-10-1997
			JP	10510808 T	20-10-1998
			WO	9618597 A	20-06-1996
US 3513212	A	19-05-1970	BE	685705 A	20-02-1967
			DE	1568867 A	02-04-1970
			FR	92062 E	
			FR	1489681 A	15-11-1967
			GB	1104508 A	
			NL	6611631 A	20-02-1967
WO 9220420	A	26-11-1992	AU	1673692 A	30-12-1992
			DE	69218194 D	17-04-1997
			DE	69218194 T	02-10-1997
			EP	0584127 A	02-03-1994
			JP	6509498 T	27-10-1994

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82